Technical Data Sheet

Article-No.: 10410

PT Proofflex Adhesive 431 CF

epoxy based adhesive (pigmented, grey, thixotropic)

Product description

PT Proofflex Adhesive 431 CF is a two component, nonylphenol-free, special filled mortar adhesive based on epoxy resin. Due to the special formulation it is very smooth in application especially on vertical areas because of thixotropic formulation. VOC <500 g/l. The bonding of PT Proofflex Adhesive 431 CF to PT Proofflex 1 and 2 is excellent.

Application areas

PT Proofflex Adhesive 431 CF is used for structural bonding of PT Proofflex 1 and PT Proofflex 2 joint tapes. Due to the special formulation and filler structure occurs an excellent bonding between adhesive and joint tape. PT Proofflex Adhesive 431 CF is a part of PT Proofflex System (Adhesive + Joint Tape).

Product advantages

- Two components
- Smooth formulation
- Perfect bonding with high strength
- Thixotropic
- Grey
- Part of Proofflex system (Adhesive + Joint Tape)
- High compressive strength
- Easy application
- · Also suitable on humid surfaces
- Mixing ratio 2:1 by weight
- Chemical resistant
- Suitable on many surfaces
- "Made in Germany"

Specification

Base : Epoxy resin, pigment, quarz sand

Color

Component A : white Component B : dark grey

Processing temperature : + 8°C up to + 30°C surface temperature

Density (23°C) mixed : approx. 1.60 g/ml

Viscosity (23°C) : thixotropic, no saging up to 15 mm

Compressive strength (EN ISO 604) : approx. 55 N/mm² (14 days 23°C)

Flexural strength (DIN EN ISO 178) : 30 – 40 N/mm² (14 days / 23°C)



Page 2

Technical Data Sheet

E-Modul (DIN EN ISO 527) : approx. 3500 N/mm² (14 days, 23°C)

Volume shrinkage : < 1.0%

Tensile strength on concrete : concrete fracture

Tensile strength on steel : > 10 N/mm² (14 days, 23°C)

Mixing ratio : 2:1 weight parts

Processing time : 8°C approx. 90 minutes

23°C approx. 60 minutes 30°C approx. 30 minutes

Article-No.: 10410

Consumption : approx. 1.6 kg/m² per mm thickness

All technical datas are measured in our laboraty.

Please take notice about the safety information and advice given on the safety data sheets and packaging labels. GISCODE: RE1

Delivery form

15 kg unit

(comp. A 10 kg + comp. B 5 kg) Article-No. 10410015

Storage

12 months (frost-free and dry, +15°C up to +25°C in original packaging).

Application

Surface preparation

The surface must be mineral, dry or slight moist, stable, solid and clean. Loose components, release agents, formwork oil, grease and other adhesive reducing layers have to be removed before the use of PT Proofflex Adhesive 431 CF. The concrete should be 3-7 weeks old before application. Damaged areas, cracks, cavities can be re-profiled with PT Proofflex Adhesive 431 CF. Perhaps a pretreatment of the surface with sand or shotblasting is necessary. An adhesive tensile strength of 1,5 N/mm² at least is required.

Material

PT Proofflex Adhesive 431 CF must be mixed in the right mixing ratio homogenously. Therefor component B is completely filled in component A. With a suitable mixing device, the material should be mixed 3 minutes at least until no color streaks are visible. We recommend to put the material in a clean vessel and mixe it again to guarantee a homogenous mixture. The mixing device should mix at low speed to avoid air in the mixture (max. 400 U/Min.).

Application in combination with PT Proofflex

The joint tape should not completely adhered with the surface if cracks or joints are bigger than 1 mm. The joint tape has to lay loose over the joint or crack. The mixed PT Proofflex Adhesive 431 CF must be applied on both sides along the joint by using a spatula or notched trowel (coating thickness of the adhesion: 1-2mm). Application width on both sides min. 40 mm.



Technical Data Sheet

Article-No.: 10410

The PT Proofflex 1 or 2 (joint tape) must be embedded within the pot life time of the PT Proofflex Adhesive 431 CF and pressed firmly in the adhesive by using a roller. It is very important to avoid air pockets in the adhesive layer, because it may cause leaks afterwards. In case of joint movement, the PT Proofflex System is layed in loop form into the joint. If the joints are smaller than 1 mm the PT Proofflex 1 or 2 Joint Tape can be fully covered with PT Proofflex Adhesive 431 CF.

Recommended tools

Brush Trowel Gloves Safety glasses Mixing equipment

Application areas:

Spraying device









Remarks

The information given in this technical data sheet corresponds to the current state of development and is based on our experience, our knowledge and is non-binding. An investigation has to be done with focus on the respective building project and the area of application. The technical expert advice of proof-tec employees does not exclude the planning or control by an engineer. We are liable within the scope of our general delivery and sales conditions, we are not liable for the application of our materials. The generally accepted rules of technology must be observed. If necessary, preliminary tests have to be carried out.

Version 02/2017

All previous versions of this technical data sheet are not valid anymore and should not be used anymore.

